



GD 116

General Properties	Technology/Base	Polysulfide
	Base - Part A	Polysulfide
	Base - Part B	Manganese dioxide
	Type of Product	Insulating glass sealant
	Curing	Two part curing
		Oxidative curing
	Colour	Black
	Product Benefits	High strength and elasticity





Typical Technical Data

Part A

Physical Properties Density Colour	1.79 g/cm ³ beige	DIN EN ISO 2811-1
Packaging Units Content	190 l	drum

Part B

Physical Properties		
Density	1.58 g/cm ³	DIN EN ISO 2811-1
Colour	black	
Packaging Units		
Content	19	hobbock
Content	190 l	drum





General

Processing Guidelines and Parameters		
Shelf Life	9 months	
Storage Temperature	10 ℃ to 30 ℃	
Mixing Ratio (Part A : Part B) by Weight	10 : 0.88	
Mixing Ratio (Part A : Part B) by Volume	10 : 1	
Processing Temperature	15 ℃ to 35 ℃	
Mixing tolerance	\pm 20%	
Curing		
Potlife	≥ 20 min	Kö-test method 100296, 23 °C
Potlife (rule of thumb)	40 min	20 ℃
Potlife (rule of thumb)	20 min	30 ℃
Potlife (rule of thumb)	10 min	40 ℃
Material Properties		
Volatile content	0.52%	EN 1279-4 annex H
Fogging	without visual	EN 1279-4 annex C
	fogging	
Cured Material Characteristics		
Shore Hardness (Type A)	≥ 40	EN 1279-6 annex E, after 24 h, 23 ℃
Adhesion float glass	0.38 MPa	EN 1279-4 annex A, crossover stress $(\sigma_{\rm C})$
Gas permeation rate (Argon)	0.002 g/(m ² ·h)	EN 1279-4 annex D
Gas permeation rate (Argon)	0.058 g/(m ² ·d)	EN 1279-4 annex D
Water vapour transmission rate	6.0 g/(m ² ·d)	EN 1279-4 annex D

Product Properties

Applications	Typical Applications	Secondary sealant for insulating glass
Processing	Suitable Substrates	Various galvanized steels
		Various stainless steel alloys
		Various aluminium alloys
		Glass
	Consistency	Pasty
	Surface Requirements	Dry
		Clean
		Free of grease
		Free of dust
	Application Equipment	Two part mixing and metering system
Cleaning	Cleaner for Tools	Körasolv GL
Certifications	Certifications and Declarations of	ASTM E2190
	Conformity	CEKAL
		EN 1279 pt. 2 + 3 + 4
		IGCC
		RAL-GZ 520 (Sealants)
		UNI certification



Interested in More Product Options? - Just Get Our App



Glass Americas

Additional Information

Storage

GD 116 should be used within the shelf life specified on the packaging. The storage stability applies to material stored under appropriate conditions only (original unopened containers, recommended storage temperature).

Safety

Please read our Safety Data Sheet (SDS) and the labels of each product before use. The valid safety regulations must be considered.

Preparation

Due to the huge variety of available substrates preliminary testing regarding adhesion and compatibility is strongly recommended.

Processing

Refer to the technical data table regarding processing parameters. Low temperatures can cause a temporary increase in viscosity resulting in reduced extrusion and slower curing rates.

Cleaning

Clean tools immediately after use. Once cured, the material can only be removed mechanically. Appropriate cleaners are listed in the product properties table. For further information please contact your local sales office.

Disposal

Please refer to the Safety Data Sheet (SDS) for disposal instructions.

IMPORTANT: Information, specifications, procedures and recommendations provided (information) are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is users sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the users intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fullers liability for fraud, gross negligence or for death or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.

Kömmerling Chemische Fabrik GmbH

Zweibrücker Straße 200 - 66954 Pirmasens - Germany

Tel.: +49 6331 56-2000 Fax: +49 6331 56-1999 www.koe-chemie.de



